

## Material 60 EPDM 334

black  
cross linking: peroxidic



**CONTACT US**

<b>Print date</b>	<b>revision index</b>	<b>revision date</b>	<b>page</b>	<b>1/1</b>
7/13/2018	3	11/21/2016		

Physical properties	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	1.02 ±0.02	1.02	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1, Shore A, 23 °C	60 ±5	60	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	---	2.5	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	> 12	14.6	MPa
<b>Elongation at Break</b> DIN 53504, S2, 23 °C	> 240	305	%
<b>Compression set</b> DIN ISO 815, B, 24 h, 150 °C, 25 %	< 30	18	%
<b>Low Temperature</b> ISO 11357-2, DSC	---	-53	°C

Specific characteristic and limitations for the use in food contact are set out in the corresponding declaration of conformities.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

**Freudenberg**  
Freudenberg Sealing Technologies  
Global Material Technology  
Wolfgang Becker

Phone: +49 (0)6201/80-2893  
Fax: +49 (0)6201/88-2893  
Email: wolfgang.becker@FST.com



## Material 60 EPDM 334

black

cross linking: peroxidic

### Print date

7/13/2018

page 1/1

### Declarations of conformity

	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
ACS	F	Seals		08 / 2020	<input type="checkbox"/>
ADI Free					<input checked="" type="checkbox"/>
Arrete 9.Nov 1994	F	Seals	food		<input checked="" type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
NSF 61	USA	Seals	Hungary		<input checked="" type="checkbox"/>
ÖNORM B 5014	A	Seals	Estonia	09 / 2021	<input type="checkbox"/>
ÖNORM B 5014	A	Seals	Hungary	09 / 2021	<input type="checkbox"/>
ÖNORM B 5014	A	Seals	Reichelsheim	09 / 2021	<input type="checkbox"/>
UBA Leitlinie	D	Course commodity	Platten/Halbzeuge Weinheim	11 / 2021	<input type="checkbox"/>
UBA Leitlinie	D	Seals	Estonia	09 / 2021	<input type="checkbox"/>
UBA Leitlinie	D	Seals	Hungary	09 / 2021	<input type="checkbox"/>
UBA Leitlinie	D	Seals	Reichelsheim	09 / 2021	<input type="checkbox"/>
W270	D	Seals	Drinking water	08 / 2020	<input type="checkbox"/>
WRAS BS 6920	GB	Seals	85 °C	04 / 2020	<input type="checkbox"/>

### Freudenberg

Freudenberg Sealing Technologies  
Global Material Technology  
Wolfgang Becker

Phone: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com