



2360 Palumbo Drive (606)269-2351
Lexington, KY 40512



CONTACT US

Date: 11/09/01
Compound: V8545-75
Batch: 40000216
Page: 1 of 1

COMPOUND DATA SHEET

	AMS 7257C Requirements	V8545-75 2-214 O-Ring Results
<u>Original Physical Properties, ASTM D1414, D2240</u>		
Hardness, (Shore A), pts.	75 ±5	78
Tensile Strength, min., psi.	1500	1895
Ultimate Elongation, min., %	120	204
<u>Fluid Resistance, AMS 3021 (70 h @ 175°C) ASTM D471</u>		
Hardness Change, pts.	-5 to +5	-2
Tensile Strength Change, max., %	-10	+7
Ultimate Elongation Change, max., %	-15	+7
Volume Change, %	0 to +5	+1.6
<u>Fluid Resistance, AS 1241 (70 h @ 125°C) ASTM D471</u>		
Hardness Change, pts.	-15 to 0	0
Tensile Strength Change, max., %	-40	-19
Ultimate Elongation Change, max., %	-15	+2
Volume Change, %	0 to +15	+2.6
<u>Fluid Resistance, ASTM Fuel B (70 h @ 23°C) ASTM D471</u>		
Hardness Change, pts.	-5 to +5	+1
Tensile Strength Change, max., %	-20	-8
Ultimate Elongation Change, max., %	-15	-5
Volume Change, %	0 to +5	+0.3
<u>Heat Age, (70 h @ 290°C) ASTM D573</u>		
Hardness Change, (Shore A), pts.	-5 to +5	-2
Tensile Strength Change, max., %	-20	-2
Ultimate Elongation Change, max., %	-5	+7
Weight Loss, max., %	5	+3.0
<u>Compression Set, (70 h @ 230°C) ASTM D395</u>		
Percent of Original Deflection, max., %	40	38
<u>TR-10, ASTM D1329</u>		
TR-10, max., °C	+5	-6