



Parker Seal De Matamoros
 Diagonal Lorenzo de la Garza #13
 Matamoros MEXICO 87490



CONTACT US

MTR NO: 220663
 Rev Date: 3/5/15
 Batch: N/A
 Part Size: 2-214
 Tested as: 2-214
 Customer: N/A
 Test Location: PSDM
 Page: 1 of 1

Specification: AMS-R-25988 & MIL-DTL-25988

Material Test Report

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>AMS-R-25988 Limit</u>	<u>MIL-DTL-25988 Limit</u>	<u>Results</u>
Hardness, Shore A Pts.	ASTM D2240	70 ± 5	70 ± 5	70
Tensile Strength, min. psi	ASTM D1414	750	750	1417
Elongation min %	ASTM D1414	125	125	278
Specific Gravity	ASTM D297	As determined	As determined	1.46
Temperature Retraction, °F, max	ASTM D1329	-70	-70	-85
Heat Resistance Test				
70 Hrs @ 392°F (200°C)				
	ASTM D573			
Hardness Change, max. pts.		+10 to -5	+4	+4
Tensile Strength, Decrease max%		-25	-9	-9
Elongation Decrease, max%		-25	-8	-8
Weight Loss, % max		2	.05	.05
Compression Set Test Method B				
70 Hrs @ 75°F (23°C)				
Over 0.110 inch	ASTM D395 B	15	8	8
Compression Set Test Method B				
22 Hrs @ 347°F (175°C)				
Over 0.110 inch	ASTM D395 B	30	7	7
	ASTM D471			
AMS 3021 Resistance Test				
70 Hrs @ 302°F (150°C)				
Hardness Change, Max pts.		±15	-3	-3
Tensile Strength, Decrease max%		-40	-20	-20
Elongation Decrease, max%		-25	-17	-17
Volume Change, max%		1 to 15	+10	+10
COMPRESSION SET, MAX%				
Over 0.110 inch		30	11	11
TT-S-735 type III resistance test				
22 Hrs @ 75°F (23°C)				
	ASTM D471			
Hardness Change, max. pts.		-20		-2
Tensile Strength, Decrease, max%		-45		-35
Elongation Decrease, max%		-35		-28
Volume Change, max%		1 to 25		+16
AMS 2629, type I resistance test				
22 Hrs. @ 75°F (23°C)				
	ASTM D471			
Hardness Change, max pts.			-20	-1
Tensile Strength, Decrease max%			-45	-33
Elongation Decrease, max%			-35	-27
Volume Change, max%			1 to 25	+17

*Purchaser use only. Reproduce only in full. Data pertains to items references only.
 The recording of false, fictitious, or fraudulent statements or entries on this report may be
 punishable as a felony under federal law.*