



MATERIAL REPORT



REPORT NUMBER: KK2205
DATE: 8/22/95

CONTACT US

TITLE: Evaluation of Parker Compound N1231-80
PURPOSE: To obtain general information.

Recommended temperature limits: -25⁰F to 300/325⁰F

Recommended For

Explosive Decompression Resistance
Petroleum based hydraulic oil, motor oil, transmission fluid,
grease
R134a
Water/glycol/steam
HFA, HFB, and HFC fluids
Ozone, aging, and weather resistance

Not Recommended For

Polar solvents (ketones and esters)
Strong acids
Chlorinated hydrocarbons
Auto and aircraft brake fluids



REPORT DATA

Report Number: KK2205

<u>Original Physical Properties</u>	N1231-80 <u>Results</u>
Hardness, Shore A, pts, 2	81
Tensile, Kg/cm, 2, min.	240
Elongation, %, min.	297
<u>Heat Aging</u>	
<u>70 Hrs. @ 150°C (302°F)</u>	
Hardness, Change, pts.	+4
Tensile, Change, %, max	-8.5
Elongation, Change, %	-20.2
<u>Compression Set</u>	
<u>70 Hrs. @ 150°C (302°F)</u>	
% of Original Deflection, max.	27.1
<u>ASTM Oil #1</u>	
<u>70 Hrs. @ 150°C (302°F)</u>	
Hardness, Change, pts	+3
Tensile, Change, %, max	+3.8
Elongation, Change, %, max	-7.1
Volume, Change, %	-1.3
<u>Sunisco 5GS Oil</u>	
<u>70 hrs. @ 150°C (302°F)</u>	
Hardness, Change, pts	-2
Tensile, Change, %, max	-1.8
Elongation, Change, %, max	-5.1
Volume, Change, %	+7.5
<u>ND8 Oil</u>	
<u>70 hrs. @ 150°C (302°F)</u>	
Hardness, Change, pts	+2
Tensile, Change, %, max	+6.1
Elongation, Change, %, max	-20.2
Volume, Change, %	-0.2
<u>Heat Age</u>	
<u>560 hrs. @ 120°C</u>	
Hardness, Change, pts	+4
Tensile, Change, %	+8.7
Elongation, %	-14.6



Compound Data Sheet
Parker O-Ring Division United States

Heat Age	N1231-80
<u>560 hrs. @ 150°C</u>	<u>Result</u>
Hardness, Change, pts	+9
Tensile, Change, %	+4.1
Elongation, %	-45.5
Heat Age	
<u>1000 hrs. @ 120°C</u>	
Hardness, Change, pts	+6
Tensile, Change, %	+2.1
Elongation, %	-17.7
Compression Set	
<u>70 hrs. @ 120°C</u>	28.9
% of Original Deflection	33.3
Compression Set	
<u>140 hrs. @ 120°C</u>	35.7
% of Original Deflection	38.9
Compression Set	
<u>140 hrs. @ 150°C</u>	71.4
% of Original Deflection	79.4
Compression Set	
<u>280 hrs. @ 120°C</u>	51.4
% of Original Deflection	55.6
Compression Set	
<u>280 hrs. @ 150°C</u>	84.3
% of Original Deflection	88.2
Compression Set	
<u>560 hrs. @ 120°C</u>	65.7
% of Original Deflection	67.6
Compression Set	
<u>560 hrs. @ 150°C</u>	
% of Original Deflection	91.4
Compression Set	
<u>1000 hrs. @ 120°C</u>	
% of Original Deflection	79