



COMPOUND DATA SHEET

Parker O-Ring & Engineered Seals Division United States

MATERIAL REPORT

Report Number: 119276
12/13/2016



[CONTACT US](#)

Title: Evaluation of Parker Compound

Elastomer Type: Butyl (IIR) B0612-70

Purpose: To obtain typical test data.

Specification: ASTM D2000 M4AA708 A13 B33 EA14 F17

Color: Black

Recommended Temperature Range: -75°F to 250°F

Recommended For: Salt solutions, polar solvents (alcohols, ketones, and esters), hot water and steam up to 250°F, brake fluids with glycol base (DOT 3 and DOT 4), many acids, poly-glycol based hydraulic fluids (HFC fluids), phosphate-ester bases (HFD-R fluids), ozone, aging, and weather resistance.

Not Recommended For: Mineral oils and grease, fuels, chlorinated hydrocarbons

Additional Approvals: None

“Purchaser use only. Reproduce only in full. Data pertains to items referenced only. The recording of false, fictitious, or fraudulent statements or entries in this report may be punishable as a felony under federal law.”

REPORT DATA

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Spec Limits</u>	<u>Results</u>
Hardness, Shore A, pts.	ASTM D2240	70±5	75
Tensile Strength, PSI (Mpa)	ASTM D412	1160 (8)	1771 (12.2)
Ultimate Elongation, %	ASTM D412	200	289

(A13) Heat Age

70 hrs. @ 158°F (70°C)

Hardness Change, pts	ASTM D573	+10	0
Tensile Strength Change, %		-25	+9
Ultimate Elongation Change, %		-25	+4

(B33) Compression Set (Plied)

22 hrs. @ 158°F (70°C)

Percent of Original Deflection, Max		35	9
-------------------------------------	--	----	---

(EA14) Fluid Resistance

Water, 70 hrs. @ 212°F (100°C)

Volume Change, %		+10	+3
------------------	--	-----	----

(F17) Low Temperature Brittleness

Nonbrittle after 3 min @ -40°C	ASTM D2137	Pass	Pass
--------------------------------	------------	------	------

(G21) Tear Strength, Die B

kN/m. min	ASTM D624	26	27
-----------	-----------	----	----